



**Society of Cable  
Telecommunications  
Engineers**

---

**ENGINEERING COMMITTEE  
Interface Practices Subcommittee**

---

**AMERICAN NATIONAL STANDARD**

**ANSI/SCTE 63 2009**

**Test Method for Voltage  
Withstand of Outer Jacket**

## NOTICE

The Society of Cable Telecommunications Engineers (SCTE) Standards are intended to serve the public interest by providing specifications, test methods and procedures that promote uniformity of product, interchangeability and ultimately the long term reliability of broadband communications facilities. These documents shall not in any way preclude any member or nonmember of SCTE from manufacturing or selling products not conforming to such documents, nor shall the existence of such standards preclude their voluntary use by those other than SCTE members, whether used domestically or internationally.

SCTE assumes no obligations or liability whatsoever to any party who may adopt the Standards. Such adopting party assumes all risks associated with adoption of these Standards or Recommended Practices, and accepts full responsibility for any damage and/or claims arising from the adoption of such Standards or Recommended Practices.

Attention is called to the possibility that implementation of this standard may require use of subject matter covered by patent rights. By publication of this standard, no position is taken with respect to the existence or validity of any patent rights in connection therewith. SCTE shall not be responsible for identifying patents for which a license may be required or for conducting inquiries into the legal validity or scope of those patents that are brought to its attention.

Patent holders who believe that they hold patents which are essential to the implementation of this standard have been requested to provide information about those patents and any related licensing terms and conditions. Any such declarations made before or after publication of this document are available on the SCTE web site at <http://www.scte.org>.

All Rights Reserved

© Society of Cable Telecommunications Engineers, Inc. 2009

140 Philips Road

Exton, PA 19341

## TABLE OF CONTENTS

1.0	SCOPE .....	1
2.0	EQUIPMENT .....	1
3.0	SPARK TESTING .....	1
4.0	REQUIREMENT .....	3
5.0	REPORT .....	3

## 1.0 SCOPE

This procedure specifies the spark test method to be used in determining if the outer jacket of a coaxial cable will withstand a specified voltage.

## 2.0 EQUIPMENT

- 2.1 A spark tester shall include a voltage source capable of maintaining the test voltage as specified in the relevant cable specification. The test fixture shall also have an electrode, a voltmeter, automatic shut-off capability in the event of arcing through the cable jacket material and must be capable of detecting, counting and signaling momentary faults.
- 2.2 The electrode shall be of chain-link or bead-chain type capable of attachment to the voltage source, and making intimate contact with the jacket of the coaxial cable under test.

## 3.0 SPARK TESTING

- 3.1 The test sample is a jacketed coaxial cable of sufficient length to be passed through the bead electrodes of the spark tester at a maximum defined rate (See Section 3.3) as it is being wound onto the cable reel.
- 3.2 The outer conductor and the center conductor of the coaxial cable being tested shall be securely bonded to ground at the payoff reel or at any other location which assures a continuous low impedance contact between the outer conductor and the center conductor of the coaxial cable being tested and ground. In addition, the spark tester shall also be securely bonded to ground.
- 3.3 Jacketed coaxial cable shall be passed through the link or bead electrode at a maximum defined rate that will insure uniform electrode contact with the moving jacketed cable. The maximum rate at which the jacketed coaxial cable passes through the bead-chain electrode shall keep any point on the jacket in contact with the bead-chain electrode for greater than 18 positive and negative crests of the AC supply voltage (9 complete cycles.) The following formulas, as applicable, may be used to calculate the coaxial cable maximum rate through the spark tester:

$$3.3.1 \quad RATE_{\max\_in} = \frac{5}{9} * f * L_{in} \text{ in feet per minute}$$

$$3.3.2 \quad RATE_{\max\_mm} = \frac{1}{150} * f * L_{mm} \text{ in meters per minute}$$

where:

$Rate_{max}$  = The maximum rate in feet per minute (3.2.1) or meters per minute (3.2.2) at which the jacketed coaxial cable may pass through the bead-chain electrode.

$f$  = Test frequency of the AC spark tester in Hertz.

$L_{in}$  = The electrode (bead Chain) length in inches (3.2.1)

$L_{mm}$  = The electrode (bead Chain) length in millimeters (3.2.2).

- 3.4 The test fixture voltage setting shall be adjusted to provide the test voltage specified as continuously indicated by the voltmeter. A fault detector will detect, indicate and count any momentary faults that occur.
- 3.5 The magnitude of voltage that is applied is proportional to the thickness of the jacket material. Table 1 below provides recommended test voltages, dependent upon the outer jacket thickness. The cable specification and / or safety listing requirements; (examples UL 1581, Paragraph 900, UL 13, Paragraph 27) shall be the final authority for the voltage setting .

**Table 1, Jacket Spark Test Voltages**

Jacket Thickness-inches (mm)	Test Voltage (kilovolts)
Less than 0.020 (0.5)	See Note 1
0.020 (0.5) to 0.030 (0.79)	2.0 kilovolts
0.031 (0.8) to 0.040 (1.0)	3.0 kilovolts
Greater than 0.040 (1.0)	5.0 kilovolts

Note 1: Samples that have a jacket thickness less than 0.020 inches (0.5 mm) should not be subjected to voltage tests.

#### **4.0 REQUIREMENT**

The cable under test shall be passed through the bead electrode of the test fixture at a defined rate less than the  $Rate_{max}$  defined in Section 3.3 as it is being wound onto the cable reel. Arcing between the spark test electrode through the cable jacket into the outer conductor shall constitute a failure. The cable under test shall exhibit no more failures per unit length than the maximum specified in the applicable coaxial cable specification.

#### **5.0 REPORT**

5.1 Each manufacturer conducting spark testing shall report the following information as a minimum on internally developed and approved forms:

- 5.1.1 The product part number;
- 5.1.2 The date of the spark test;
- 5.1.3 The jacket type i.e., PVC or PE;
- 5.1.4 The Voltage level;
- 5.1.5 The number of indicated faults.